



TruTuf

Zirconia toughened Alumina

Product Data Sheet		
Characteristics	Unit	TruTuf
Composition: <i>Alumina and Zirconia</i>		
Density	g/cm ³	≥ 4.10
Abrasion Resistance	cm ³ .h ⁻¹	0.02
Vickers Hardness	HV - N/mm ²	1350
Fracture Toughness	MN.m ^{-$\frac{2}{3}$}	5.1

Remarks:

The table above illustrates typical physical and chemical characteristics of the products listed and may vary depending on method of manufacture, size and shape.

